



## Status of U.L. approvals, Product Certified for Canada included

LATI S.p.A. - updated - November 2009

file LATI: E 54080 - QMFZ2 , QMFZ8

### UL FOOTNOTES

- |   |  |
|---|--|
| <p>(a) indicates glass loadings from 1-30 percent</p> <p>(b) indicates glass loadings from 6-34 percent</p> <p>(c) indicates glass loadings from 5-30 percent</p> <p>(d) indicates glass loadings from 1-29 percent</p> <p>(e) indicates glass loadings from 20-40 percent</p> <p>(f2) Subjected to one or more of the following tests:<br/>Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL Inc.</p> <p>(g) indicates glass loadings from 26-49 percent</p> <p>(h) indicates glass loadings from 16-34 percent</p> <p>(i) indicates glass loadings from 10-30 percent</p> <p>(k) indicates glass loadings from 20-30 percent</p> | <p>(l) indicates glass loadings from 16-29 percent</p> <p>(m) indicates glass loadings from 16-24 percent</p> <p>(n) indicates glass loadings from 26-34 percent</p> <p>(p) indicates glass loadings from 36-49 percent</p> <p>(s) indicates glass loadings from 11-49 percent</p> <p>(q) Optional marking consisting of a generic indication of color (English or Italian) followed by an alphanumeric code (consisting of 4 digits and 1 letter) indicating color shade.</p> <p>(r) Optional marking consisting of an alphanumeric code (consisting of 1 or 2 letters followed by one number) referring to manufacturing process information.</p> <p>(u) recognition valid up to 50% regrind</p> <p>(@) all color except black</p> |
|---|--|



(1-30) indicates MFI from 1-30 g/10<sup>1</sup>  
LATI Products listed in UL file E54080 meet US and Canadian requirements.

Product	Material	Colors	Min Thk mm	UL 94 Flame Class	R.T.I.											
					Elec		Mech		H W I	H A I	H V T R	D 4 9 5	C T I	G W T	G W I	
					With Imp	w/o Imp	Imp	Imp								
PA66	Latamid 66 (q) (r)	ALL	0.75	V-2	65	65	65	-	-	-	-	-	-	-	-	-
	Latamid 66 PX15 (q) (r)	BK	0.75	HB	105	80	100	4	0	-	-	-	-	-	-	-
	Latamid 66 H2 G/25 (q) (r)	ALL	1.50	HB	105	80	110	2	0	-	-	-	-	-	-	-
			3.00	HB	105	80	110	1	0	1	6	1	-	-	-	-
	Latamid 66 H2 G/(g) (q) (r) (see notes)	ALL	0.75	HB	105	80	100	4	0	-	-	-	-	-	-	-
			3.00	HB	105	80	105	1	0	1	6	1	-	-	-	-
	Latamid 66 H2 G/30 (q) (r)	ALL	0.75	HB	105	80	100	4	0	-	-	-	-	-	-	-
			1.50	HB	105	80	105	2	0	1	-	-	-	-	-	-
	Latamid 66 H2 G/50 (q) (r)	ALL	3.00	HB	105	80	105	1	0	1	6	1	-	-	-	-
			0.75	HB	105	85	100	3	0	-	-	-	-	-	-	-
	Latamid 66 H2 G/60 (q) (r)	BK	1.50	HB	105	85	105	1	0	-	-	-	-	-	-	-
			3.00	HB	105	85	105	0	0	0	6	0	-	-	-	-
	Latamid 66 VH2 G/15 (q) (r)	NC,BK	0.75	HB	130	110	130	3	0	-	-	-	-	-	-	-
			1.50	HB	130	120	130	2	0	-	-	-	-	-	-	-
	Latamid 66 VH2 G/(m) (q) (r)(see notes)	NC,BK	3.00	HB	130	120	130	0	0	1	6	2	-	-	-	-
			0.75	HB	115	90	120	4	0	-	-	-	-	-	-	-
	Latamid 66 VH2 G/25 (q) (r)	NC,BK	1.50	HB	120	95	120	2	0	-	-	-	-	-	-	-
			3.00	HB	125	95	125	0	0	0	6	2	-	-	-	-
	Latamid 66 VH2 G/(n) (q) (r) (see notes)	NC,BK	0.71	HB	115	90	120	4	0	-	-	-	-	-	-	-
			1.50	HB	120	95	120	2	0	-	-	-	-	-	-	-
	Latamid 66 VH2 G/30 (q) (r)	ALL	3.00	HB	125	95	125	0	0	0	6	2	-	-	-	-
			0.71	HB	115	90	120	4	0	-	-	-	-	-	-	-
	Latamid 66 VH2 G/35 (q) (r)	NC,BK	1.50	HB	120	120	120	1	0	-	-	-	-	-	-	-
			3.00	HB	125	120	125	0	0	0	6	1	-	-	-	-
	Latamid 66 VH2 G/(p) (q) (r) (see notes)	NC,BK	0.71	HB	115	115	120	4	0	-	-	-	-	-	-	-
			1.50	HB	120	120	120	1	0	-	-	-	-	-	-	-
	Latamid 66 VH2 G/50 (q) (r)	NC,BK	3.00	HB	125	120	125	0	0	0	6	1	-	-	-	-
			0.71	HB	115	120	120	4	0	-	-	-	-	-	-	-
	Latamid 66 S/30 (q) (r)	ALL	1.50	HB	120	120	120	0	0	-	-	-	-	-	-	-
			3.00	HB	125	120	125	0	0	0	6	1	-	-	-	-

Product Material		R.T.I.												
		Colors		Elec		Mech		H W	H A	H V	D 4	C T	G W	G W
				Min Thk mm	UL 94 Flame Class	With Imp	w/o Imp							
Kelon A H CE/40 (q) (r)	ALL	0.71	HB	120	95	120	4	0	-	-	-	-	-	
		1.50	HB	120	95	120	2	0	-	-	-	-	-	
		3.00	HB	125	95	125	3	0	3	6	1	-	-	
Latamid 66 H-V0 (q) (r)	NC	0.41	V-0	65	65	65	-	-	-	-	-	-	-	
		0.81	V-0	125	75	75	4	0	-	-	-	-	-	
		1.50	V-0	125	75	75	3	0	-	-	-	-	-	
Latamid 66 H2PX30-V0 (q) (r)	ALL	0.41	V-0	125	80	85	1	0	0	5	0	-	-	
		0.71	V-0	65	65	65	-	-	-	-	-	-	-	
		0.40	V-2	65	65	65	-	-	-	-	-	-	-	
Latamid 66 H2PX-V0 (q) (r)	NC,WT,RD	0.75	V-0	65	65	65	4	0	-	-	-	-	-	
		0.75	V-1	65	65	65	4	0	-	-	-	-	-	
		1.00	V-0	65	65	65	4	0	-	-	-	775	960	
Latamid 66 H2PX-V0 (q) (r)	BK	1.00	V-1	65	65	65	4	0	-	-	-	775	960	
		1.50	V-0	65	65	65	3	0	-	-	-	775	960	
		2.00	V-0	65	65	65	3	0	-	-	-	775	960	
Latamid 66 BH-V0 (q) (r)	ALL	0.75	V-0	65	65	65	0	0	-	-	-	-	-	
		0.75	V-2	65	65	65	-	-	-	-	-	-	-	
		1.00	V-2	65	65	65	-	-	-	-	-	850	850	
Latamid 66 H2PX-V2 (q) (r)	ALL	2.00	V-2	65	65	65	-	-	-	-	-	850	960	
		3.00	V-2	65	65	65	-	-	-	-	-	850	960	
		0.75	V-0	65	65	65	-	-	-	-	-	-	-	
Latamid 66 BG/20-V (q) (r)	ALL	0.75	V-0	65	65	65	-	-	-	-	-	-		
Latamid 66 G/20-V0 (q) (r)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	
		0.81	V-0	110	80	95	4	0	-	-	-	-	-	
Latamid 66 H2 G/05-V0 (q) (r)	ALL	1.50	V-0	110	80	100	2	0	-	-	-	-	-	
		3.00	V-0	110	80	105	1	0	1	6	2	-	-	
		0.81	V-0	110	80	95	4	-	-	-	-	-	-	
Latamid 66 H2 G/(b)-V0 (q) (r) (see notes)	ALL	1.50	V-0	110	80	100	2	0	-	-	-	-	-	
		3.00	V-0	110	80	105	1	0	1	6	2	-	-	
		0.81	V-0	110	85	110	4	0	-	-	-	-	-	
Latamid 66 H2 G/25-V0 (q) (r)	ALL	1.50	V-0	110	85	110	2	0	-	-	-	-	-	
		3.00	V-0	110	85	110	1	0	1	6	2	-	-	
		0.81	V-0	115	105	110	0	1	-	-	-	-	-	
Latamid 66 H2 G/35-V0 (q) (r)	ALL	1.50	V-0	115	105	120	0	0	-	-	-	-	-	
		3.00	V-0	115	105	120	0	0	1	6	2	-	-	
		0.75	V-0	100	75	75	3	0	-	-	-	-	-	
Latamid 66 H2 G/25-V0KB (q) (r)	NC,BK	1.50	V-0	100	80	80	1	0	-	-	-	-	-	
		3.00	V-0	100	85	85	1	0	1	6	1	-	-	
		0.75	V-0	105	75	75	3	0	-	-	-	-	-	
Latamid 66 H2 G/35-V0KB (q) (r)	NC,BK	1.50	V-0	105	85	85	1	0	-	-	-	-	-	
		3.00	V-0	105	85	85	1	0	1	6	1	-	-	
		0.75	HB	105	75	75	2	0	-	-	-	-	-	
Latamid 66 H2 G/15-V0KB1 (q) (r)	ALL	1.50	V-0	105	75	75	1	0	-	-	-	-	-	
		3.00	V-0	105	85	85	0	0	1	6	1	-	-	
		0.75	HB	130	115	140	3	0	-	-	-	-	-	
Latamid 66 H2 G/(h)-V0KB1 (q) (r) (see notes)	ALL	1.50	V-0	130	115	140	1	0	-	-	-	-	-	
		3.00	V-0	130	115	140	0	0	1	6	1	-	-	
		0.75	HB	130	115	150	3	0	-	-	-	-	-	
Latamid 66 H2 G/35-V0KB1(q) (r)	ALL	1.50	V-0	130	115	150	1	0	-	-	-	-	-	
		3.00	V-0	130	115	150	0	0	1	6	0	-	-	
		0.86	V-0	110	100	115	0	1	-	-	-	-	-	
Latamid 66 H2 G/50-V0KB1 (q) (r)	NC,BK	1.00	V-0	110	105	120	0	1	-	-	-	800	960	
		1.50	V-0	110	105	120	0	1	-	-	-	800	960	
		2.00	V-0	110	105	120	0	1	-	-	-	800	960	
		3.00	V-0	110	105	120	0	1	0	6	0	800	960	
Latamid 66 H2 G/25-V0KB3 (q) (r)	NC,BK,GY	0.75	HB	110	100	120	2	0	-	-	-	-	-	
		1.50	V-0	110	100	120	0	0	-	-	-	-	-	
		3.00	V-0	110	110	120	0	0	1	5	0	-	-	
Latamid 66 H2 G/35-V0KB3 (q) (r)	NC,BK	1.50	V-0	130	115	140	0	0	-	-	-	-	-	
		3.00	V-0	130	115	140	0	0	0	5	0	-	-	
		0.75	V-0	-	130	130	0	0	-	-	-	-	-	
Latamid 66 H2 G/25-V0KB4 (q) (r)	NC,BK, GY,GN	0.90	V-0	130	130	130	0	0	-	-	-	-	-	
		1.00	V-0	130	130	130	0	0	-	-	-	775	960	
		2.00	V-0	130	130	130	0	0	-	-	-	800	960	
		3.00	V-0	130	130	130	0	0	-	-	0	800	960	

Product Material		R.T.I.													
		Colors	Min Thk mm	UL 94 Flame Class	Elec		Mech		H W I	H A I	H V T R	D 4 9 5	C T I	G W I	G W I
					With Imp	w/o Imp	With Imp	w/o Imp							
Latamid 66 H2 G/25-V0CT1 (q) (r)	NC	0.40	V-2	65	65	65	-	-	-	-	-	-	-	-	
	NC, BK	0.50	V-2	130	65	65	0	0	-	-	-	-	-	-	
	ALL	0.71	V-0	140	120	130	0	0	-	-	-	-	850	960	
		1.50	V-0	140	120	130	0	0	-	-	-	-	850	960	
		2.00	V-0	140	120	130	0	0	-	-	-	-	900	960	
Latamid 66 H2 G/25-V0HF1 (q) (r)	GY	3.00	V-0	140	120	130	0	0	1	6	1	900	960		
		0.50	HB	65	65	65	-	-	-	-	-	-	-		
	ALL	0.75	V-0	-	130	130	0	0	-	-	-	-	-		
		0.90	V-0	130	130	130	0	0	-	-	-	-	-		
1.50		V-0	130	130	130	0	0	-	-	-	775	960			
Latamid 66 H2 G/25-V0HF (q) (r)	ALL	3.00	V-0	130	130	130	0	0	-	-	0	800	960		
Latamid 66 H2 G/20-V2 (q) (r)	ALL	0.75	V-0	65	65	65	-	-	-	-	-	-	-		
		0.75	V-2	65	65	65	-	-	-	-	-	-	-		
		1.00	V-2	65	65	65	-	-	-	-	-	800	960		
Kelon A FR H2 CEG/250-V0 (q) (r)	ALL	2.00	V-2	65	65	65	-	-	-	-	-	900	960		
		3.00	V-2	65	65	65	-	-	-	-	-	900	960		
		0.74	HB	65	65	65	-	-	-	-	-	-	-		
Kelon A FR H2 CETG/300-V0 (q) (r)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-		
		0.74	V-0	130	100	120	0	0	-	-	-	-	-		
	ALL	1.00	V-0	130	100	120	0	0	-	-	-	850	960		
		1.10	V-0	130	100	120	0	0	-	-	-	-	-		
Kelon A FR H2 CET/35-V2 (q) (r)	ALL	1.50	V-0	130	100	130	0	0	-	-	-	850	960		
		3.00	V-0	130	100	130	0	0	2	6	2	900	960		
		0.71	V-2	140	100	140	0	0	-	-	-	-	-		
Kelon A FR H2 CER/25-V2HF (q) (r)	ALL	1.50	V-2	140	100	140	0	0	-	-	-	800	960		
		3.00	V-2	140	105	140	0	0	0	5	1	825	960		
PA66/6 Latamid 68 H2-V0 (q) (r)	ALL	0.80	V-2	65	65	65	-	-	-	-	-	-	-		
		0.41	V-0	65	65	65	4	0	-	-	-	-	-		
		0.71	V-0	140	95	110	4	0	-	-	-	-	-		
		0.7-0.8	V-0	140	95	110	4	0	-	-	-	960	960		
		1.50	V-0	140	95	110	3	0	-	-	-	-	-		
Latamid 68 H2-V0H (q) (r)	RD,BK	3.00	V-0	140	95	110	2	0	0	6	0	-	-		
		0.75	V-0	130	105	130	4	0	-	-	-	-	-		
		1.50	V-0	130	105	130	3	0	-	-	-	-	-		
		2.00	V-0,5VA	130	105	130	3	0	-	-	-	-	-		
PA6 Latamid 6 (q) (r)	NC,BK	3.00	V-0,5VA	130	105	130	1	0	1	6	3	-	-		
		0.75	V-2	65	65	65	-	-	-	-	-	-	-		
		0.75	V-2	140	90	115	4	0	-	-	-	-	-		
		Latamid 6 BH (q) (r)	ALL	1.50	V-2	140	95	115	4	0	-	-	-	-	
		3.00	V-2	140	95	115	3	0	0	5	0	-	-		
		Latamid 6 H2 G/10 (q) (r)	ALL	0.75	HB	130	115	140	4	0	-	-	-	-	
				1.50	HB	130	115	140	4	0	-	-	-	-	
		Latamid 6 H2 G/30 (q) (r)	ALL	3.00	HB	130	130	155	4	0	-	5	1	-	
				0.71	HB	65	65	65	-	-	-	-	-	-	
				0.75	HB	125	115	140	-	-	-	-	-	-	
		Latamid 6 H2 G/(s) (q) (r)	ALL	1.50	HB	125	115	140	4	0	-	-	-	-	
				3.00	HB	125	125	155	4	0	0	5	1	-	
				0.75	HB	125	115	140	4	0	-	-	-	-	
		Latamid 6 H2 G/50 (q) (r)	ALL	1.50	HB	125	120	150	4	0	-	-	-	-	
				3.00	HB	125	125	155	4	0	0	5	0	-	
		Kelon B H CET/30 (q) (r)	ALL	0.71	HB	140	105	140	4	0	-	-	-	-	
				1.50	HB	140	105	140	-	-	-	-	-	-	
Kelon B H CETG/300 (q) (r)	ALL	3.00	HB	140	105	140	3	0	0	6	1	-			
		1.50	HB	65	65	65	-	-	-	-	-	-			
Latamid 6 H2 PX-V0 (q) (r)	NC	NC	NC	NC	NC	NC	NC	NC	NC	NC	NC	NC			
		1.00	V-0	65	65	65	-	-	-	-	-	800	960		
		2.00	V-0	65	65	65	-	-	-	-	-	800	960		
Latamid 6 H-V0 (q) (r)	ALL	3.00	V-0	65	65	65	-	-	-	-	-	800	960		
		0.40	V-2	65	65	65	-	-	-	-	-	-			
		0.86	V-0	140	105	120	4	0	-	-	-	-			
Latamid 6 H-V0 (q) (r)	ALL	1.50	V-0	140	105	120	2	0	-	-	-	-			
		3.00	V-0	140	105	120	2	0	0	6	0	-			

Product Material		R.T.I.													
		Colors	Min Thk mm	UL 94 Flame Class	Elec		Mech		H W I	H A I	H V T R	D 4 9 5	C T I	G W I T	G W F I
					With Imp	w/o Imp	With Imp	w/o Imp							
Latamid 6 H2 PX-V2 (q) (r)	NC	0.75	V-2	65	65	65	-	-	-	-	-	-	-	-	-
		1.00	V-2	65	65	65	-	-	-	-	-	-	-	825	850
		2.00	V-2	65	65	65	-	-	-	-	-	-	-	825	900
		3.00	V-2	65	65	65	-	-	-	-	-	-	-	825	900
Latamid 6 G/20-V1 (q) (r)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	-	
Latamid 6G/(k)-V1 (q) (r) (see notes)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	-	
		3.00	V-0	65	65	65	-	-	-	-	-	-	-	-	
Latamid 6 G/30-V1 (q) (r)	ALL	1.50	V-1	65	65	65	-	-	-	-	-	-	-	-	
Latamid 6 H2 G/15-V0 (q) (r)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	-	
Latamid 6 H2 G/(l)-V0 (q) (r) (see notes)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	-	
Latamid 6 H2 G/30-V0 (q) (r)	ALL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	-	
Latamid 6 H2 G/20-V2HF (f2) (q) (r)	ALL	0.75	V-2	120	115	115	2	0	-	-	-	-	-	-	
		1.50	V-2	120	120	120	2	0	-	-	-	-	-	-	
		3.00	V-2	120	120	120	2	0	1	6	1	-	-	-	
Latamid 6 H2 G/(k)-V2HF (q) (r)	ALL	0.75	V-2	120	115	115	2	0	-	-	-	-	-	-	
		1.50	V-2	120	120	120	2	0	-	-	-	-	-	-	
		3.00	V-2	120	120	120	2	0	1	6	1	-	-	-	
Latamid 6 H2 G/30-V2HF (q) (r)	ALL	0.75	V-2	130	120	120	2	0	-	-	-	-	-	-	
		1.50	V-2	130	120	130	1	0	-	-	-	-	-	-	
		3.00	V-2	130	120	130	0	0	1	6	1	-	-	-	
Latamid 6 H2 G/30-V0CT1 (q) (r)	ALL	0.75	V-0	130	115	130	0	0	-	-	-	-	-	-	
		1.50	V-0	130	115	130	0	0	-	-	-	-	-	-	
		3.00	V-0	130	115	130	0	0	1	5	1	-	-	-	
Latamid 6 H2 G/30-V0HF1 (q) (r)	ALL	0.75	V-0	-	130	130	0	0	-	-	-	-	-	-	
		0.90	V-0	130	130	130	0	0	-	-	-	-	-	-	
		1.00	V-0	130	130	130	0	0	-	-	-	-	775	960	
		2.00	V-0	130	130	130	0	0	-	-	-	-	775	960	
Kelon B FR H2 CE/25-V2HF (q) (r)	ALL	0.70	V-2	65	65	65	-	-	-	-	-	-	-	-	
		0.71	V-2	65	65	65	-	-	-	-	-	-	-	-	
		0.71	V-2	140	105	140	0	0	-	-	-	-	-	-	
Kelon B FR H CET/30-V0 (q) (r)	ALL	1.50	V-0	140	105	140	0	0	-	-	-	-	-	-	
		3.00	V-0	140	105	140	0	0	0	6	1	-	-	-	
		0.75	V-0	140	120	140	0	0	-	-	-	-	-	-	
Kelon B FR H CETG/250-V0 (q) (r)	ALL	1.50	V-0	140	120	140	0	0	-	-	-	-	-	-	
		3.00	V-0	140	120	140	0	0	0	6	2	-	-	-	
		0.75	V-1	150	105	130	-	-	-	-	-	-	-	-	
Kelon B FR H2 CEG/500-V0CT3 (q) (r)	ALL	1.20	V-0	150	110	140	0	0	-	-	-	-	-	-	
		3.00	V-0	150	120	140	0	0	-	-	0	-	-	-	
		0.70	V-2	65	65	65	-	-	-	-	-	-	-	-	
PPA Laramid G/30-V0HF1 (q) (r)	ALL	0.75	V-0	50	50	50	0	2	-	-	-	-	-	960	
		1.50	V-0	50	50	50	0	1	-	-	-	-	-	960	
		3.00	V-0	50	50	50	0	1	-	6	0	825	960	-	
PP Latene AG7H G/30 (q) (r)	ALL	1.50	HB	65	65	65	-	-	-	-	-	-	-	-	
		0.75	HB	65	65	65	-	-	-	-	-	-	-	-	
		1.50	HB	65	65	65	-	-	-	-	-	-	-	-	
		1.5-2.7	HB	65	65	65	-	-	-	-	-	-	-	-	
		1.5-2.7	HB	65	65	65	-	-	-	-	-	-	-	-	
		1.50	HB	65	65	65	-	-	-	-	-	-	-	-	
		3.00	HB	65	65	65	-	-	-	-	-	-	-	-	
		1.80	V-0	65	65	65	-	-	-	-	-	-	-	-	
		0.75	V-2	65	65	65	-	-	-	-	-	-	-	-	
		1.50	V-2	65	65	65	-	-	-	-	-	-	-	-	
		3.00	V-2	65	65	65	-	-	-	-	-	-	-	-	
		0.75	V-2	65	65	65	-	-	-	-	0	-	-	-	
		1.00	V-2	65	65	65	-	-	-	-	-	775	960	-	
		2.00	V-2	65	65	65	-	-	-	-	-	775	960	-	
		2.10	V-2	65	65	65	-	-	-	-	-	-	-	-	
		0.55	V-2	65	65	65	4	0	-	-	-	-	-	-	
		0.45	V-2	65	65	65	4	0	-	-	-	-	-	-	
		1.00	V-2	65	65	65	4	0	-	-	-	-	825	960	
		1.50	V-0	110	115	115	2	0	-	-	-	-	825	960	
		3.00	V-0	110	115	115	1	0	1	6	0	825	960	-	
		1.50	V-0	110	115	115	2	0	-	-	-	-	-	-	
		3.00	V-0	110	115	115	1	0	1	6	0	-	-	-	
1.50	V-0	110	115	115	2	0	-	-	-	-	-	-			
3.00	V-0	110	115	115	1	0	1	6	0	-	-	-			
1.50	V-0	110	115	115	2	0	-	-	-	-	-	-			
3.00	V-0	110	115	115	1	0	1	6	0	-	-	-			

Product Material		R.T.I.													
		Colors	Min Thk mm	UL 94 Flame Class	Elec		Mech		H W I	H A I	H V T R	D 4 5	C T I	G W I T	G W F I
					With Imp	w/o Imp	With Imp	w/o Imp							
	Latene 30H2W-V0 (q) (r)	ALL	1.50	V-0	110	115	115	2	0	-	-	-	-	-	
		ALL	3.00	V-0	110	115	115	1	0	1	6	0	-	-	
	Latene 7H2W T-V0 (q) (r)	ALL	0.75	V-0	100	100	100	3	0	1	-	-	-	-	
		ALL	1.50	V-0	100	100	100	3	0	1	-	-	-	-	
		ALL	3.00	V-0	100	100	100	2	0	1	6	0	-	-	
		WT, GY	2.00	5VA	100	100	100	3	0	-	-	-	-	-	
	Latene 7H2W T-V0E (q) (r)	ALL	0.75	V-0	65	65	65	4	2	-	-	-	-	-	
		ALL	1.50	V-0	65	65	65	3	0	-	-	-	-	-	
		ALL	2.00	V-0,5VB	65	65	65	3	0	-	-	-	-	-	
		ALL	3.00	V-0,5VB	65	65	65	2	0	-	-	-	-	-	
	Latene 7 T-V0 (q) (r)	NC	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
		NC	3.00	V-0	65	65	65	-	-	-	-	-	-	-	
	Latene 7 G/25-V0 (q) (r)	NC	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
	Latene AG3H2W G/30-V0 (q) (r)	ALL	0.89	V-0	65	65	65	-	-	-	-	-	-	-	
		ALL	3.00	5VA	65	65	65	-	-	-	-	-	-	-	
	Latene AG3H2W G/30-V0(f2) (q) (r)	BK	3.00	-	65	65	65	-	-	-	-	-	-	-	
	Latene AG7H2 G/30-V0HF (q) (r)	BK	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
	Latene EP 7-V2 (q) (r)	ALL	1.50	V-2	65	65	65	-	-	-	-	-	-	-	
	Latene EP 3H-V0 (q) (r)	YL	1.50	V-0	65	65	65	-	-	-	-	-	-	-	
ABS	Lastilac SP G/05 (q) (r)	ALL	1.50	HB	60	60	60	-	-	-	-	-	-	-	
	Lastilac SP G/ (c) (q) (r) (see notes)	ALL	1.50	HB	60	60	60	-	-	-	-	-	-	-	
	Lastilac SP G/30 (q) (r)	ALL	1.50	HB	60	60	60	-	-	-	-	-	-	-	
	Lastilac RT-HB (q) (r)	ALL	1.50	HB	60	60	60	-	-	-	-	-	-	-	
		ALL	1.50	HB	60	60	60	-	-	-	-	-	-	-	
	Lastilac RT S/20 (q) (r)	ALL	3.00	HB	60	60	60	-	-	-	-	-	-	-	
	Latilac AR-V0 (q) (r)	ALL	1.50	V-0	60	60	60	-	-	-	-	-	-	-	
		ALL	3.30	5VA	60	60	60	-	-	-	-	-	-	-	
	Latilac AR-V0E (q) (r)	ALL	1.50	V-0	60	60	60	-	-	-	-	-	-	-	
		ALL	3.00	V-0	60	60	60	-	-	-	-	-	-	-	
	Latilac ARUV-V0 (q) (r)	ALL	1.70	V-0	60	60	60	3	0	-	-	-	-	-	
		ALL	3.30	5VA	60	60	60	2	0	3	6	1	-	-	
	Lastilac TR1-V0 (q) (r)	NC	1.70	V-0	60	60	60	-	-	-	-	-	-	-	
	Lastilac AR G/(d)-V0 (q) (r) (see notes)	ALL	1.50	V-0	60	60	60	-	-	-	-	-	-	-	
	Lastilac AR G/30-V0 (q) (r)	ALL	1.50	V-0	60	60	60	-	-	-	-	-	-	-	
Alloys	Lastilac 11 G/10 (q) (r)	NC	1.50	HB	60	60	60	-	-	-	-	-	-	-	
	Lastiflex AR-V0 (q) (r)	ALL	0.71	V-0	50	50	50	-	-	-	-	-	-	-	
		ALL	3.00	5VA	50	50	50	-	-	-	-	-	-	-	
PS	Lastirol R-V0 (q) (r)	NC	1.60	V-2	50	50	50	-	-	-	-	-	-	-	
		NC	3.00	V-0	50	50	50	-	-	-	-	-	-	-	
	Lastirol R-V2 (q) (r)	NC	1.60	V-2	50	50	50	-	-	-	-	-	-	-	
	Lastirol TR G/10-V1 ES (q) (r)	NC	3.00	V-2	50	50	50	-	-	-	-	-	-	-	
		NC	6.00	V-1	50	50	50	-	-	-	-	-	-	-	
	Lastirol TR G/10-HB ES (q) (r)	NC, BK	1.50	HB	50	50	50	-	-	-	-	-	-	-	
PPOm	Laril 13-V1 (q) (r)	NC, BK	1.50	V-1	50	50	50	-	-	-	-	-	-	-	
	Laril 13-V1KC (q) (r)	GY	1.50	V-1	50	50	50	-	-	-	-	-	-	-	
		GY	6.00	V-0	50	50	50	-	-	-	-	-	-	-	
	Laril 13 G/(a)-V1 (q) (r) (see notes)	NC	1.50	V-1	50	50	50	-	-	-	-	-	-	-	
		NC	6.00	V-0	50	50	50	-	-	-	-	-	-	-	
	Laril 13 G/20-V1 (q) (r)	GY,NC, BK	1.50	V-1	50	50	50	-	-	-	-	-	-	-	
		NC	6.00	V-0	50	50	50	-	-	-	-	-	-	-	
PC	Latilon 24D-V2 (q) (r)	ALL	1.00	V-2	80	80	80	-	-	-	-	-	-	-	
		ALL	2.50	V-2	80	80	80	-	-	-	-	-	-	-	
	Latilon 26D-V2 (q) (r)	ALL	1.00	V-2	80	80	80	-	-	-	-	-	-	-	
		ALL	2.50	V-2	80	80	80	-	-	-	-	-	-	-	
	Latilon 28D-V2 (q) (r)	ALL	1.00	V-2	80	80	80	-	-	-	-	-	-	-	
		ALL	2.50	V-2	80	80	80	-	-	-	-	-	-	-	
	Latilon 30D-V2 (q) (r)	ALL	1.00	V-2	80	80	80	-	-	-	-	-	-	-	
		ALL	2.50	V-2	80	80	80	-	-	-	-	-	-	-	
	Latilon 28-V0 (q) (r)	ALL	0.89	V-2	80	80	80	-	-	-	-	-	-	-	
		ALL	3.00	V-0	80	80	80	-	-	-	-	-	-	-	
	Latilon 28D-V0 (q) (r)	ALL	0.89	V-2	80	80	80	-	-	-	-	-	-	-	
		ALL	3.00	V-0	80	80	80	-	-	-	-	-	-	-	
	Latilon 30-V0 (q) (r)	NC	0.91	V-2	80	80	80	-	-	-	-	-	-	-	
		NC	1.70	V-0	80	80	80	-	-	-	-	-	-	-	
	Latilon 30D-V0 (q) (r)	NC	0.91	V-2	80	80	80	-	-	-	-	-	-	-	
		NC	1.70	V-0	80	80	80	-	-	-	-	-	-	-	

Product	Material	Colors	Min Thk mm	UL 94 Flame Class	R.T.I.								G W I T	G W I F I	
					Elec		Mech		H W I	H A I	H V T R	D 4 9 5			C T I
					With Imp	w/o Imp	80	80							
	<b>Latilon 28D G/(e) (q) (r)</b> (see notes)	ALL	1.50	V-1	80	80	80	-	-	-	-	-	-	-	
			6.00	V-0	80	80	80	-	-	-	-	-	-	-	
	<b>Latilon 30D G/10-V0 (q) (r)</b>	ALL	0.89	V-2	80	80	80	-	-	-	-	-	-	-	
			1.70	V-0	80	80	80	-	-	-	-	-	-	-	
	<b>Latilon 28D G/20-V0</b>	GN	0.60	HB	80	80	80	-	-	-	-	-	-	-	
		ALL	1.50	V-0	80	80	80	-	-	-	-	-	-	-	
<b>PBT</b>	<b>Later 4 G/15 (q) (r)</b>	ALL	0.75	HB	140	130	140	4	0	-	-	-	-	-	
			1.50	HB	140	130	140	2	0	-	-	-	-	-	
			3.00	HB	140	130	140	0	0	0	5	2	-	-	
	<b>Later 4 G/(l) (q) (r)</b> (see notes)	ALL	0.75	HB	130	130	140	4	0	-	-	-	-	-	
			1.50	HB	130	130	140	2	0	-	-	-	-	-	
			3.00	HB	130	130	140	0	0	1	6	2	-	-	
	<b>Later 4 G/30 (q) (r)</b>	ALL	0.75	HB	130	130	140	3	0	-	-	-	-	-	
			1.50	HB	130	130	140	1	0	-	-	-	-	-	
			3.00	HB	130	130	140	0	0	1	6	1	-	-	
	<b>Later 4 CE/50 (q) (r)</b>	NC	0.71	HB	75	75	75	-	-	-	-	-	-	-	
	<b>Later 4-V0 (q) (r)</b>	ALL	0.75	V-0	140	130	140	4	0	-	-	-	-	-	
			1.50	V-0	140	130	140	3	0	-	-	-	-	-	
			3.00	V-0	140	130	140	2	0	4	6	2	-	-	
	<b>Later 4 G/10-V0 (q) (r)</b>	ALL	0.75	V-0	130	120	120	4	0	-	-	-	-	-	
			1.50	V-0	130	120	120	3	0	-	-	-	-	-	
			3.00	V-0	130	130	130	2	0	4	6	2	-	-	
	<b>Later 4 G/(i)-V0 (q) (r)</b> (see notes)	ALL	0.75	V-0	130	120	120	4	0	-	-	-	-	-	
			1.50	V-0	130	120	120	3	0	-	-	-	-	-	
			3.00	V-0	130	130	130	2	0	4	6	2	-	-	
	<b>Later 4 G/30-V0 (q) (r)</b>	ALL	0.75	V-0	140	130	130	3	0	-	-	-	-	-	
			1.50	V-0	140	130	130	2	0	-	-	-	-	-	
			3.00	V-0	140	130	140	0	0	4	6	2	-	-	
	<b>Later 4 G/30-V0CT1 (q) (r)</b>	NC	0.75	V-0	75	75	75	-	-	-	-	-	-	-	
			1.50	V-0	75	75	75	-	-	-	-	-	-	-	
			3.00	V-0	75	75	75	-	-	-	5	1	-	-	
	<b>Later 4 G/30-V0CT2 (q) (r)</b>	NC	0.75	V-0	75	75	75	-	-	-	-	-	-	-	
			1.00	V-0	75	75	75	0	2	-	-	-	-	-	
			1.50	V-0	75	75	75	0	2	-	-	-	930	960	
			3.00	V-0	75	75	75	0	1	-	-	-	930	960	
			3.00	V-0	75	75	75	0	0	-	6	0	960	960	
	<b>Later 4 G/30-V0HF1 (q) (r)</b>	ALL	0.75	V-0	75	75	75	0	1	-	-	-	-	-	
			1.00	V-0	75	75	75	0	1	-	-	-	825	960	
			1.50	V-0	75	75	75	0	0	-	-	-	825	960	
			3.00	V-0	75	75	75	0	0	-	5	0	960	960	
	<b>Later 4E61 GCER/450-V0 (q) (r)</b>	GY	0.75	V-0	75	75	75	3	0	-	-	-	-	-	
			1.50	V-0	75	75	75	2	0	-	-	-	-	-	
			3.00	V-0	75	75	75	1	0	0	4	1	-	-	
<b>POM</b>	<b>Latan 9 (q) (r)</b>	NC	1.50	HB	50	50	50	-	-	-	-	-	-	-	
	<b>Latan 13 S/30 (q) (r)</b>	ALL	1.50	HB	50	50	50	-	-	-	-	-	-	-	
<b>PPS</b>	<b>Larton G/40 (q) (r)</b>	NC, BK	0.42	V-0	130	130	130	-	-	-	-	-	-	-	
			0.75	V-0	130	130	130	5	0	-	-	-	-	-	
			1.50	V-0	130	130	130	4	0	-	-	-	-	-	
			3.00	V-0	130	130	130	0	0	-	-	-	-	-	
	<b>Larton GCE/600 (q) (r)</b>	NC, BK	0.75	V-0	130	130	130	3	1	-	-	-	-	-	
			1.50	V-0	130	130	130	3	1	-	-	-	-	-	
			3.00	V-0	130	130	130	0	1	-	-	-	-	-	
	<b>Larton GCE/650 (q) (r)</b>	ALL	0.75	V-0	130	130	130	3	3	-	-	-	-	-	
			1.50	V-0	130	130	130	0	0	-	-	-	-	-	
			3.00	V-0	130	130	130	0	0	-	-	-	-	-	
	<b>Larton L G/40 (q) (r)</b>	NC	0.75	V-0	130	130	130	-	-	-	-	-	-	-	
<b>PSU</b>	<b>Lasulf (q) (r)</b>	ALL	1.50	HB	50	50	50	-	-	-	-	-	-	-	

Product Material		Colors	Min Thk mm	UL 94 Flame Class	R.T.I.								G W I T I	G W F I	
					Elec		Mech		H W I	H A I	H V T R	D 4 9 5			C T I
					With Imp	w/o Imp	With Imp	w/o Imp							
<b>SPECIALS</b>															
PA6	Latilub 62-01M G/30 (q) (r)	NC, (BK)	0.86	HB	65	65	65	-	-	-	-	-	-	-	
PA66	Latilub 66-20T G/20 (q) (r)	ALL	0.75	HB	120	100	110	3	0	-	-	-	-	-	
			3.00	HB	120	100	115	0	0	0	6	0	-	-	
			0.72	HB	65	65	65	-	-	-	-	-	-	-	-
	Latilub 66-01M (q) (r)	NC	0.72	HB	65	65	65	-	-	-	-	-	-	-	
	Latilub 66-01M G/(a) (q) (r) (see notes)	NC	0.72	HB	65	65	65	-	-	-	-	-	-	-	
	Latilub 66-01M G/30 (q) (r)	NC	0.72	HB	65	65	65	-	-	-	-	-	-	-	
PA12	Latamid 12 H FE90:0081 (q) (r)	NC,(BK)	0.71- 3.00	HB	65	65	65	-	-	-	-	-	-	-	
PC	Latilub 87/28-20T (q) (r)	NC,BK	1.50	HB	80	80	80	-	-	-	-	-	-	-	
			3.00	V-1	80	80	80	-	-	-	-	-	-	-	
			6.00	V-0	80	80	80	-	-	-	-	-	-	-	
		Latilub 87/24UV-20T (q) (r)	GY	0.75	HB	80	80	80	-	-	-	-	-	-	
		Latilub 87/28-12T G/20 (q) (r)	NC,BK	1.40	HB	80	80	80	-	-	-	-	-	-	
			3.00	V-1	80	80	80	-	-	-	-	-	-		
			6.00	V-0	80	80	80	-	-	-	-	-	-		
POM	Latilub 73/13-20T (q) (r)	NC,BK	1.50	HB	50	50	50	-	-	-	-	-	-	-	
	Latilub 73/13-15T G/15 (q) (r)	NC	1.50	HB	50	50	50	-	-	-	-	-	-	-	
			3.00	HB	50	50	50	-	-	-	-	-	-	-	
PPS	Latilub 80-15T G/30 (q) (r)	NC,BK	0.74	V-0	130	130	130	-	-	-	-	-	-	-	
PA/PP	Latiblend 6252 H2 G/30 (q) (r)	ALL	0.75	HB	50	50	50	-	-	-	-	-	-	-	
PA6	Latiohm 63-08 PD02 G/25 (q) (r)	BK	0.75	HB	65	65	65	-	-	-	-	-	-	-	
			3.00	HB	65	65	65	-	-	-	-	-	-	-	
PA6	Laticonther 62 CEG/500-V0HF1 (q) (r)	ALL	0.75	V-1	150	105	130	-	-	-	-	-	-	-	
			1.20	V-0	150	110	140	0	0	-	-	-	-	-	
			3.00	V-0	150	120	140	0	0	-	-	0	-	-	
<b>REMARKS</b>															
LATI does not guarantee that the data contained in this list are current, complete and error-free. To double check the values, users are kindly requested to contact LATI Technical Assistance or commercial network. LATI Industria Termoplastici S.p.A. declines all responsibility arising from any use of the information described in this document.															
Copyright © 1999 LATI S.p.A. - All Rights Reserved															